



Longwrap

Technical Data Sheet

DESCRIPTION	<p>Longwrap Petrolatum Tape is a 1.15 mm VOC Free, cold applied, wax based tape designed to protect piping and metal structures from damage and deterioration caused by corrosion at temperatures up to 70°C (158°F). This multi-environment coating is appropriate for use below grade in dry, damp or wet operating conditions. The Longwrap Petrolatum Tape encapsulates the surface in order to protect it, this allows for easy inspection of the substrate and repair of the coating. The tape is used with the Longwrap Paste which completely wets out the substrate surface and displaces any moisture.</p> <p>Longwrap Petrolatum Tape is a highly moldable protective coating that will easily conform to irregular contours and difficult to coat structures. It is available in both a Temperate and Tropical grade.</p>
SUBSTRATE COMPATIBILITY	Steel, Stainless Steel, Ductile Iron, Other Metals, FBE, PE, PP, Concrete
RECOMMENDED USE	Ideal for protecting structures such as fittings, flanges, valves, mechanical couplings, vault piping and other complex piping and metal structures.
SURFACE PREPARATION	SSPC SP-2 Hand Tool Cleaning
PRIMER	Longwrap Petrolatum Tape requires a primer to ensure maximum effectiveness of the system. Apply a minimum of 4 mils of Longwrap Paste using a gloved hand or by mechanical means. The Longwrap Petrolatum Tape can be applied immediately following the primer application.
OPTIONAL OUTERWRAP	To seal the system before burial the Longwrap Petrolatum Tape can be wrapped with Maflowrap PVC Outerwrap. This Outerwrap will add abrasion and UV resistance to the Longwrap Petrolatum Tape.
REFERENCE	<p>Longwrap Petrolatum Tape and the Longwrap Paste together meet all of the performance criteria listed in the most recent revisions of:</p> <p>NACE RP0375 (Cold-Applied Wax-Tape Coating System) ANSI/AWWA C217</p>
SAFETY	Refer to Material Safety Data Sheet: MSDS-Longwrap-Tape, MSDS-Longwrap-Paste
APPLICATION	Refer to Application Guidelines: AG-COLD-APPLIED-LONGWRAP-PET-WAX-TAPES

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Protective Coatings Ltd
 Harbour Road,
 Rye, East Sussex, TN31 7TE, UK
 Phone: +44(0)1797.223561
 Fax: +44(0)1797.224530
 www.chasecorp.com
 A BS EN ISO 9001:2008
 REGISTERED COMPANY

Chase Corporation
 295 University Avenue
 Westwood, MA 02090
 Phone: 800-323-4182
 Fax: 781-332-0701
 www.chasecorp.com
 An ISO 9001:2008
 REGISTERED COMPANY

LONGWRAP PETROLATUM TAPE TYPICAL DATA

Property	Metric	US Customary	Test Method
Color	Brown	Brown	
VOC Content	0 g/l	0 lb/gal	
Total Thickness	1.15 mm	45 mils	ASTM D1000
Cathodic Disbondment, 30 days	<5 mm radius	<0.2 in ²	ASTM G8
Dielectric Strength	16 kV (2 layers)	16 kV (2 layers)	ASTM D149
Tensile Strength	4.0 N/mm	22.8 lb/in	ASTM D1000
Storage Temperature Range	<50°C	<122°F	
Application Temperature Range Temperate Grade Tropical Grade	+5°C to +45°C +5°C to +55°C	+41°F to +113°F +41°F to +131°F	
Service Temperature Range Temperate Grade Tropical Grade	up to 55°C up to 70°C	up to 131°F up to 158°F	

LONGWRAP PASTE TYPICAL DATA

Property	Metric	US Customary	Test Method
Color	Brown	Brown	
VOC Content	0 g/l	0 lb/gal	
Service Temperature Range	-29°C to 121°C	-20°F to 250°F	

ORDERING INFORMATION

Longwrap Tape

Dimension	Sizes Available
Width	50, 75, 100, 150, 225, 300 mm
Length	10 m

Longwrap Paste

Container Size	Weight
Pail	2.5 kg